



Substrate		DIN 60001	100 % polyester
Weave		DIN ISO 9354	knitted fabric
Weight approx.		DIN EN ISO 2286-2	210 g/m ²
Shrinkage*		190°C, 180 s	warp: ≤ 4,5 % weft: ≤ 2,5 %
Fire retardancy		DIN 4102 B1	yes
Application			indoor
Width		DIN EN ISO 2286-1	max. 310 cm / 122 inch (see overview)
Print side			width < 3 m: print side outside width > 3 m: print side inside
Roll length			30 - 70 ± 0,5 m
Type of ink		<input type="checkbox"/> SUB <input type="checkbox"/> UV <input type="checkbox"/> LATEX	sublimation inks, UV-curable inks, latex inks

Advantages

- scratch-resistant reverse side
- fast crease recovery
- stretchable
- soft
- opaque
- trimming cold (no fraying)

Applications

- banner
- blockout
- frame tensioning systems

* shrinkage has to be tested before printing; recommended processing temperature: 180°C; 30-45 s



All details are nominal values and are subject to change within usual tolerances (± 5 %). The information provided in this document is based on current knowledge and experience. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor. date: 01/2020